



Product Specification

Product Name:

PORTER'S DUCHESS SATIN

PRODUCT DESCRIPTION:

Porter's Duchess Satin is a pearlescent paint used to decorate walls with the rich luster of satin fabric. Create a delicate pearly glitter on walls, trims, architraves or furniture. As visible brushstrokes are a characteristic of pearlescent paints, application methods will vary end results.

LOCATION:

Interior.

ENVIRONMENTAL INFORMATION:

This product contains: 68g/L VOC.

APAS* Target level for this product: 80g/L.

Porter's Paints use only premium grade, low odour, minimal environmental impact raw materials, and wherever possible we buy from Australian suppliers. Our manufacturing processes are zero waste, and all paint formulations are designed for maximum performance with minimum impact on user health.

* Australian Paint Approval Scheme.

SUGGESTED APPLICATIONS:

Can be applied to most suitably prepared plasterboard, plaster, wood, masonry and previously painted surfaces.

COLOURS:

Choose from our large range of colours, or ask our colourist for your own custom colour.

LIMITATIONS:

Visible brushstrokes are a characteristic of pearlescent paints and it is for this reason that we do not recommend application with a paint roller. Do not apply in high humidity, below 10°C or above 30°C.

PREPARATION:

NEW/UNPAINTED SUBSTRATES:

Substrate should be a clean well-held surface free from loose material, dirt, grease, oil and mould. Dust down before proceeding.

On bare surfaces such as new unpainted plasterboard sheeting, render brick or timber, spot

prime all joints and repaired areas with Porter's Limeproof Undercoat Sealer, then apply two coats of same to entire area. Touch dry 2 hours. Allow 6 hours dry time per coat.

On new unpainted fresh set plaster do not proceed until plaster has thoroughly set and has dried completely. Firstly, apply 1 coat Porter's Mineral Silicate Primer by brush or roller. Touch dry 20 minutes. Allow 2 hours dry time. Then apply by brush, roller or spray 1 coat Porter's Limeproof Undercoat Sealer. Touch dry 2 hours. Allow 6 hours dry time.

PREVIOUSLY PAINTED SUBSTRATES:

Previously painted surfaces with loose, peeling or flaking paint must be made sound by scraping off loose paint. Fill nail holes and cracks with suitable filler, sand and dust off. Spot prime all joints and repaired areas with Porter's Limeproof Undercoat Sealer, then apply two coats of Porter's Limeproof Undercoat Sealer.

APPLICATION:

By brush – may be applied in a random brush finish, or a smooth dragged finish. For a random brush finish, apply two coats using a “crows feet” brushing technique, cutting in progressively. For a smooth dragged finish, apply paint in a vertical direction, cutting in progressively, then with a dry brush lay off over finished work while paint is still wet to achieve an even appearance. Do not “picture frame” a wall, cutting in should be completed progressively. Touch dry 3 hours. Recoat in 12 hours. Allow 12 hours dry time.

By spray – Best results are achieved using a HVLP (high volume, low pressure) air spray. When spraying paint may be thinned with water to

a maximum of 5%. Two coats recommended. Touch dry 3 hours. Recoat in 12 hours. Allow 12 hours dry time.

Application tip – There is another application method that eliminates brush strokes and gives a beautiful mother-of pearl finish. Paint on the first coat by brush or spray as above. Allow 12 hours dry time. For the second coat two people are needed. The first person paints on the Duchess Satin, using a “crows feet” brushing technique, cutting in progressively, and the second person follows closely behind “ragging” the paint with muslin cloth. Do not go back over completed work. Do not stop in the middle of a wall. All work should be arranged to allow completion at a natural division such as a corner. Touch dry 3 hours. Allow 12 hours dry time.

COVERAGE RATES:

Covers approximately 8m² per litre, depending upon porosity, surface texture and wastage rates.

WASH UP:

Water.

COMPLEMENTARY PRODUCTS:

Porter's Limeproof Undercoat Sealer (coverage 12m² per litre) is recommended where an undercoat/primer is required when preparing substrate for painting.

Mineral Silicate Primer (coverage 10m² per litre) is recommended for priming new set plaster before undercoating.

PACKAGING:

Porter's Duchess Satin is available in 500ml, 1 litre, 2 litre, 4 litre & 15 litre sizes.

Phone: (02) 9698-5322

Toll free: 1800 656 664

Fax: (02) 9699-5322

E-mail: enquiries@porters.com.au

Web: www.porterspains.com

STORAGE:

Store in a cool dry area, protected from frost.

PRECAUTIONS:

Keep out of reach of children. Avoid swallowing. Avoid eye contact. Avoid prolonged skin contact. Provide adequate ventilation. If accidental contact occurs, rinse immediately with water. Check colour before use.

WARRANTY:

Porter's Duchess Satin has a warranty of 11 years. Porter's Paints Pty Ltd warrants this product to be of the highest quality. The information supplied here is in good faith. There are no implied conditions or warranty in the supply of this product. The manufacturer's guarantee is limited to product replacement only and does not include preparation or application.

MANUFACTURER'S/DISTRIBUTOR'S DETAILS:

Porter's Paints Pty Ltd
895 Bourke St
Waterloo NSW 2017
Australia